



Traffic and Zone Marking Paint Latex
1081,5

Product Description:

Latex Traffic & Zone Marking Paint is a glare free, non-toxic paint to be used for designating all types of lanes and zones in factories. The yellow can be used successfully as an athletic field marking paint that is free of lead hazards.

Recommended Use:

Suitable for line marking on pavement zones, lanes, identification of traffic aisles in factories and warehouses or athletic surfaces.

Application:

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

For zone marking, clean the surface of all dirt, dust, grease, oil or other contaminants. Thin with a small amount of water only if necessary. Athletic field grass should be short and dry for proper application. Thin with up to one gallon of water to 3 gallons of paint for this application.

Architectural Specifications:

NA

Precautions:

Material should not be thinned with organic solvent. Surface and air temperature should be above 50°F during drying.

Safety Information:

KEEP FROM FREEZING. Keep out of reach of children. Do not take internally. Close container after each use.

Product Specifications:

Type: Vinyl Acrylic Latex
Exposure: Interior or Exterior
Specular Gloss: 2 @ 60° ±2
Volume Solids: 34.1 % ±2
Solids by Weight: 51.0 % ±2
Vehicle: 63.0 % ±2
Pigment: 37.0 % ±2
Dry Film Thickness: 1.5 mils
Viscosity @ 77 °F: 107 KU ±5
Maximum VOC: 150 g/liter
Flash Pt °F: Non-combustible
Thinner: Water
Clean Up: Soap & Water

Available Colors and Bases:

White Yellow

Available Package Sizes:

Gallon 5 Gallon

(Weight Per Gallon: 11.2 lbs. ± .5 lb)

Drying Times:

To Touch: .5 hrs.
To Handle: 2 hrs.
To Recoat: 2 hrs.

(@ 70-77 °F, 50% R.H.)

Surface Spread Rate:

Smooth: 350-400 s.f./gal.
Porous: 250-300 s.f./gal.

(Spray Application is 50% of above)

Tools and Equipment:

Brush - Synthetic, Nylon or Polyester

Roller - 3/8" Nap Synthetic Fiber

Airless Spray - .017 to .019 Tip