



Ox-O-Deck® Multipurpose Enamel 708XX

Product Description:

This smooth flowing abrasion resistant gloss oil modified urethane/alkyd finish is suitable for use for industrial flooring, machinery or equipment on new or previously painted surfaces. Ox-O-Deck is suitable for frequent repeated heavy abrasion, including mechanical wear and repeated frequent scrubbing with cleaners or scouring agents. This all-purpose enamel will withstand repeated washings without injury to the paint and can be readily recoated when necessary.

Recommended Use:

Ramps, Stairs, Landings, Machinery, Equipment, Pipes, Railings, Industrial Flooring

Application:

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

All surfaces should be clean, dry and free from grease, wax, oil and loose or flaking previous coatings.

Unfinished Concrete Surfaces - Should be allowed to cure for 30 days before any finish is applied. Steel troweled concrete (glassy smooth) or concrete floors with heavy alkaline deposits should be mechanically abraded to obtain proper adhesion. Porous or dusty concrete should be primed with an alkali resistant primer such as Stonite Masonry Conditioner. Steel troweled smooth concrete or concrete with a hardener or curing membrane may require abrasion to obtain proper adhesion.

New Wood - Should be dry and clean.

Previously Painted Surfaces - All loose or poorly adhered previous coatings should be removed back to the original surface. Old paints should be sanded lightly and wiped clean to insure adhesion. Spot prime bare areas with Ox-O-Deck and allow to dry over night before finish-coating with this Enamel.

Architectural Specifications:

- Wood: 2 coats California Ox-O-Deck Multipurpose Enamel 708XX
Concrete, Non-Porous Masonry: 2 coats California Ox-O-Deck Multipurpose Enamel 708XX
Porous Masonry and Block: 1 coat Mason-Cote® Block Filler 3751, 1 or 2 coats California Ox-O-Deck Multipurpose Enamel 708XX
Ferrous Metal - Un-primed: 1 coat Larcoloid® Industrial Rust Inhibiting Metal Primer 21150, 1 or 2 coats California Ox-O-Deck Multipurpose Enamel 708XX

Precautions:

Do not add water, oils or mix with other paint types. Do not apply when air or surface temperature is below 50°F or when drying conditions are poor. Do not apply to concrete below ground or directly on moist ground without thoroughly etching. Inadequate ventilation, high humidity, low temperatures or thick applications will greatly retard drying time. Several thin coats provide a better finish. Not recommended for commercial garage or factory floors where lift trucks are used. California Tuf-Quik® or Tile-Cote Enamel are recommended for these heavy duty areas.

CAUTION: All coated walking surfaces can become more slippery when the surface becomes wet or contaminated by dirt, oils, food, beverage residues or other debris. To help reduce the possibility of slipping on a dry, clean walking surface, add one pint of #1000 Slip Resistant Additive or #2 Pumice per gallon of enamel before application. To attain the best possible skid resistance, coated areas must be kept dry, properly cleaned and maintained.

Safety Information:

CAUTION! COMBUSTIBLE! Use only with adequate ventilation. Keep out of reach of children. Do not take internally. Close container after each use.

Product Specifications:

Type: Oil Modified Urethane
Exposure: Interior or Exterior
Specular Gloss: 80@ 60° ± 5
Volume Solids: 56.9 % ± 2
Solids by Weight: 72.2 % ± 2
Vehicle: 70.3 % ± 2
Pigment: 29.7 % ± 2
Dry Film Thickness: 2 mils
Viscosity @ 77 °F: 82 KU ± 5
Maximum VOC: 340 g/liter
Flash Pt °F: 103
Thinner:
Clean Up: Mineral Spirits

Available Colors and Bases:

White Pastel
Medium Deep
14 Stock

Available Package Sizes:

Quart Gallon

(Weight Per Gallon: 9.9 lbs. ± .5 lb)

Drying Times:

To Touch: 4-6 hrs.
To Handle: 24 hrs.
To Recoat: 24 hrs.

(@ 70-77 °F, 50% R.H.)

Surface Spread Rate:

Smooth: 400-450 s.f./gal.
Porous: 250-300 s.f./gal.

(Spray Application is 50% of above)

Tools and Equipment:

Brush - Synthetic, Nylon or Polyester

Roller - 3/8" Nap Synthetic Fiber

Airless Spray - .017 to .019 Tip