

Trouble Shooter Linseed/Alkyd Oil Base Wood Primer - 227 Series

Product Description

This unique exterior primer provides a superior performance base coat for all latex and oil base finishes. It is formulated for maximum breathability and resists tannin and sugar bleed staining from most exterior woods including pressboard siding and rust stains from nail heads.

Recommended Use

Clapboards, shingles, shakes, shutters, pressed board, trim.

General Surface Preparation

Wood surfaces must be dry, clean and free of dust, dirt and other contaminants. Scrub all mildewed surfaces with an EPA registered Mildew solution. Rinse thoroughly with clean water and allow to dry. Wear rubber gloves and safety goggles for personal protection during this process. Seal all knots, resin deposits or gummy areas with Wipe-Out® II Alkyd Stain Block 20100. Fill all nail holes, joints and cracks with exterior Spackle or an appropriate caulking compound. Remove old paint, which is blistered, checked or cracked, back to bare wood. Spot prime all exposed wood. Prime ferrous metal surfaces with Everlive® Rust Inhibiting Metal Primer F106xx after rust and mill scale are removed.

Application

Stir with a lifting motion to fully incorporate the pigments into the linseed oil. This product is of proper consistency as packaged to be applied without thinning under normal environmental conditions. Clean tools and equipment as soon as possible with mineral spirits. Do not brush out excessively but remove any sags or runs before material has started to dry. To hold back bleeding on heavily stained areas, a second coat of primer may be necessary but should not be applied until initial coat has completely dried.

Clean up

Clean tools and equipment with mineral spirits or turpentine. Do not use water on natural bristle or china bristle brushes.

Architectural Specifications

New Wood, Clapboards, Shingles, Shakes, Windows, Trim, Plywood:
1 coat Troubleshooter Fast Drying Exterior Wood Primer 22700 White (or 22795 Neutral Base)
1 or 2 coats California or Latex or Oil House Paint in desired finish

*Note: Use Troubleshooter Fast Drying Alkyd Primer Neutral Base (22795) tinted to appropriate dark colors under darker colors.

Precautions

Surfaces to which primer is to be applied must be dry to touch. Do not apply on damp, humid or foggy days, when rain is imminent or in late afternoon when there is a threat of moisture condensing on the paint film. In hot weather do not apply material in direct sunlight, but work on the shady side of the structure if possible. Air and surface temperature should be 45°F or higher during application and drying time. Low temperatures or high humidity will greatly lengthen the normal drying time. Do not mix with other paints, special thinners or water.

The maximum period of time this primer can be exposed to weather prior to topcoating is 60 days. Primers not topcoated within 60 days should be power-washed and reprimed prior to application of finish coats. Troubleshooter Alkyd/Linseed Oil Wood Primer is resistant to the deteriorating action of mildew and bacteria. No claim is made for the preservative action to other than the paint film.

Environmental Health and Safety Information

CAUTION! COMBUSTIBLE! Use only with adequate ventilation. KEEP OUT OF REACH OF CHILDREN. Do not take internally. Close container after each use.

Trouble Shooter Linseed/Alkyd Oil Base Wood Primer - 227 Series

Trouble Shooter Linseed/Alkyd Oil Base Wood Primer - 227 Series

*Depending upon color choice, non zero VOC colorant added to this product may significantly increase VOC levels.

WARNING: This product contains a chemical known to the State of California to cause cancer, birth defects or other reproductive harm.

Lead Warning ! - If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

Working with flammables and combustibles: Fire extinguishers, a safety shower, and fire blankets must be immediately available. Use only explosion-proof electrical equipment, including lighting. Do not leave any material or equipment unattended.

All equipment must be grounded and non-sparking tools and appropriate footwear should be used.

Some paint products may contain chemicals which are harmful if they come in contact with exposed skin. Protection for exposed skin (gloves, protective creams) should be available, and used per product directions.

Always use any paint product with proper ventilation. Provide general dilution or local exhaust ventilation in volume and pattern to keep the air contaminant concentration below the applicable exposure limit (OSHA PEL) of the components being used. This information is listed on the appropriate Material Safety Data Sheets. All application areas should be ventilated in accordance with applicable OSHA regulations, contact your local office for specific information.

In an enclosed area and as required, always wear an appropriate, properly fitted respirator (NIOSH/MSHA approved) during and after application of any coating unless air monitoring demonstrates that vapor/mist levels are below applicable limits. Follow respirator manufacturer's directions for respirator use.

CAUTION! Combustible Liquid: Keep away from heat and flame. Close container after each use. Use only with adequate ventilation. Wash thoroughly after handling. In case of spillage, absorb with inert material and dispose of in accordance with applicable regulations. KEEP OUT OF REACH OF CHILDREN.

USE COMPLETELY OR DISPOSE OF PROPERLY: Dispose of in accordance with applicable Federal, State and Local regulations. Under the Resource Conservation and Recovery Act (RCRA) regulations, it is the responsibility of the product user to determine, at the time of disposal, whether a material should be classified as a hazardous waste. For recycling guidance of any unused amount, contact your local or provincial organization of recovery, recycling and disposal for regulations.

Place the rags in an empty metal container that has a tight metal lid such as a paint or stain can. Fill the container with water until the rags are submerged; Fill Place the metal

Technical Data	
Product Type	Primer
Exposure	Exterior
Specular Gloss	2° ± 2
Volume Solids	59.2% ± 2
Weight Solids	78.5% ± 2
Vehicle Solids	42.6% ± 2
Pigment	57.5% ± 2
Wet Film Thickness	4.5 mils
Dry Film Thickness	2.45 mils
Viscosity @ 77 °F	92KU ± 5
Max VOC	350 g/l
Flash Point ° F	103°F
Thinner	Mineral Spirits
Clean - up	Mineral Spirits
Surface Spread Rate	
Smooth	350-400 s.f./gal.
Porous	250-300 s.f./gal.
<i>(Spray Application is 50% of above)</i>	
Drying Times	
To Touch	4 hours
To Handle	6 hours
To Recoat	4 hours
To Wash	N/A
<i>(@ 70 - 77 °F, 50% R.H)</i>	
Surface Temperature At Application	
Maximum: Over 45°F	Maximum: Under 90°F
Storage Temperature	
Store Between Over 35°F to Under 100°F	
Tools & Equipments	
Brush	China Bristle
Roller	3/8" - 1/2" Nap
Airless Spray	.011 to 0.013 Tip
Available Package Sizes	
5 Gallon	Quart
Gallon	
<i>(Weight Per Gallon:12.2 lbs. ± .5 lb)</i>	
Available Colors and Bases	
Available in 0 stock colors	

Trouble Shooter Linseed/Alkyd Oil Base Wood Primer - 227 Series

lid tightly over the water soaked formerly combustible rags. Place lid tightly on container. Contact local municipal offices for disposal directions. Never dump solvent down any household or external drains or in any open water.

Notes

Air and surface temperature should be 45°F or higher during application and drying time. Low temperatures or high humidity will greatly lengthen the normal drying time. Do not mix with other paints, special thinners or water.

The maximum period of time this primer can be exposed to weather prior to topcoating is 60 days. Primers not topcoated within 60 days should be power-washed and reprimed prior to application of finish coats. Troubleshooter Alkyd/Linseed Oil Wood Primer is resistant to the deteriorating action of mildew and bacteria. No claim is made for the preservative action to other than the paint film.